

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 2000-044236

(43)Date of publication of application : 15.02.2000

(51)Int. Cl.

C01G 15/00
G02F 1/1343
H01B 5/14
H01B 13/00

(21)Application number : 10-208948

(71)Applicant : HOYA CORP

(22)Date of filing : 24.07.1998

(72)Inventor : MORITA KIYOSHI
OTA HIROMICHI
HOSONO HIDEO
KAWAZOE HIROSHI**(54) ARTICLE HAVING TRANSPARENT CONDUCTIVE OXIDE THIN FILM AND ITS PRODUCTION****(57)Abstract:**

PROBLEM TO BE SOLVED: To obtain an oxide film having excellent transmitting property for blue light while reducing the amt. of In_2O_3 which is a scarce mineral resource by using an oxide having a specified compsn. of Zn, Al and Ba, In as a target and specifying the substrate temp. and pressure.

SOLUTION: An oxide expressed by the general formula of $\text{Zn}_x\text{M}_y\text{In}_z\text{O}_{(x+3y/2+3z/2)}$ is used as a target to form an oxide film by sputtering or laser ablation method under the conditions of from room temp. to 300°C substrate temp. and 1×10^{-2} to 10 (Pa) pressure. In the formula, M is at least one element of Al and Ga, the proportion x/y ranges 0.2 to 12, the proportion z/y ranges 0.4 to 1.4. The conductivity of the oxide of the target is good when the carrier electron density in the conductive band ranges about 1×10^{18} to $1 \times 10^{22}/\text{cm}^3$. By injecting actions to the oxide, carrier electrons are injected to the conductive band to develop the conductivity.